

## SNOWTACK™ SE782G B

**SNOWTACK™ SE782G B** is a 58% solids, solvent free, water-borne tackifier dispersion.

The resin component is a high grade stabilized rosin ester designed to provide superior adhesive performance to a wide range of substrates. The dispersion is alkylphenol ethoxylate (APE) free and has a fine particle size with a narrow distribution curve.

### Application

**SNOWTACK™ SE782G B** is a tackifier dispersion for formulating into water based adhesives to boost peel and tack properties. Primary application is for pressure sensitive adhesives for label and tape applications. This includes paper and filmic labels, and construction, automotive and specialty tapes.

- ▲ Compatible with a range of polymers including acrylics, SBR and natural rubber
- ▲ Balance of cohesion, peel and tack performance
- ▲ Improves adhesion to high and low energy surfaces
- ▲ Good water resistance
- ▲ APE free

### Typical properties

Property	Value	Unit	Test Method
Solids	58	%	Oven drying; 45 min. 135 °C
Viscosity	400	mPa.s	Brookfield, #3, @50 rpm, 20 °C
pH	9	---	pH electrode, 20°C
Sieve Residue	<100	ppm	100 micron filter
Particle Size (AVG)	0.6	micron	Laser diffraction analyzer
Density	1.0	g/ml	25°C
Softening Point	83	°C	Mettler (dried down dispersion)
Acid Value	<20	mg KOH/g	Titration (dried down dispersion)
Glass Transition Point	34	°C	DSC (dried down dispersion)
<b>Sustainability</b>			
Bio-Renewable Content	97	%	Mass ratio

Updated 25 June 2025 by MA

### Packaging

**SNOWTACK™ SE782G B** can be available in 200kg drum and IBC's 1000kg.

### Shelf life and storage conditions

Shelf life is typically 9 months from the date of production. The product should be stored at between 5°C and 35°C and avoid freezing and direct sunlight. Product should be kept sealed to avoid risk of bacteria or fungal contamination from the air.

® and ™ Licensed trademarks of Lawter, Inc.

#### Disclaimer

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.